

UNCLASSIFIED

AD NUMBER

ADB001851

LIMITATION CHANGES

TO:

Approved for public release; distribution is unlimited.

FROM:

Distribution authorized to U.S. Gov't. agencies and their contractors; Foreign Government Information; NOV 1974. Other requests shall be referred to Canadian Embassy, 501 Pennsylvania Avenue, NW, Washington, DC 20001.

AUTHORITY

DND ltr dtd 18 Mar 1975

THIS PAGE IS UNCLASSIFIED

THIS REPORT HAS BEEN DELIMITED  
AND CLEARED FOR PUBLIC RELEASE  
UNDER DOD DIRECTIVE 5200.20 AND  
NO RESTRICTIONS ARE IMPOSED UPON  
ITS USE AND DISCLOSURE.

DISTRIBUTION STATEMENT A

APPROVED FOR PUBLIC RELEASE;  
DISTRIBUTION UNLIMITED.

AD B001851

RESEARCH AND DEVELOPMENT BRANCH  
DEPARTMENT OF NATIONAL DEFENCE  
CANADA


# DEFENCE RESEARCH ESTABLISHMENT OTTAWA

DREO TECHNICAL NOTE NO. 74-30  
DREO TN 74-30

AD No. \_\_\_\_\_  
DDC FILE COPY

MOLYBDENUM - DOPED MANGANESE DIOXIDE FOR  
USE IN LOW TEMPERATURE BATTERY CATHODES

by  
T. Våland



PROJECT NO.  
54-80-08

NOVEMBER 1974  
OTTAWA

UNCLASSIFIED

REPORT NO:

DREO TECHNICAL NOTE NO. 74-30

PROJECT NO:

54-80-08

TITLE:

Molybdenum - Doped Manganese Dioxide for Use in  
Low Temperature Battery Cathodes

AUTHOR:

T. Valand

DATED:

November 1974

SECURITY GRADING:

UNCLASSIFIED INITIAL DISTRIBUTION: December 1974

2 - DSIS Circ

Plus

- 1 - DSIS Report Collection
- 1 - Doc. Section (microfiche)
- 1 - DREO
- 1 - DREV
- 1 - CRC
- 1 - DREA
- 1 - DREP
- 1 - AECL

1 - CDLS/L, CDR

1 - NRC/CB Library, Mr. Wolchuk

1 - DAES

1 - NRC/REED

1 - Advisory Committee on Electrical  
Power Sources for Military Applications

1 - NRC/CISTI

1 - National Library

1 - Centre de Recherche Industrielle du Quebec

BRITAIN

MINISTRY OF DEFENCE

2 - DRIC

Plus

12 - Ministry of Defence (Army) Serial 17

UNITED STATES

3 - DEFENSE DOCUMENTATION CENTER

3 - SENIOR STANDARDIZATION REP. US ARMY

Plus

2 - US Army Electronics Command  
Fort Monmouth, N.J. 00302

RESEARCH AND DEVELOPMENT BRANCH

DEPARTMENT OF NATIONAL DEFENCE  
CANADA

(14) DREF-TN-74-30

DEFENCE RESEARCH ESTABLISHMENT OTTAWA

(9) TECHNICAL NOTE NO. 74-30

(6)

MOLYBDENUM-DOPED MANGANESE DIOXIDE FOR  
USE IN LOW TEMPERATURE BATTERY CATHODES,

by

(10) T. Valand

Electrical Power Sources Division

elk

(12) 16p.

(11) Nov 74

PROJECT NO.  
54-80-08

RECEIVED NOVEMBER 1974  
PUBLISHED NOVEMBER 1974  
OTTAWA

\*DRB Research Fellow 1971-72 from Norwegian Defence Research Establishment.

74-345

404 576



#### ABSTRACT

↙  
A study of the chemical and electrochemical properties of manganese dioxide cathodes containing molybdenum trioxide is described. The manganese dioxide was made by the decomposition of a dissolved mixture of manganous nitrate and a small quantity of molybdenum trioxide.

It was found that the chemical composition of the manganese dioxide was affected by the presence of less than 1% molybdenum trioxide. In certain cases, considerable improvement was observed in the discharge behaviour of electrodes made with these oxides. The doped cathodes were assessed in the  $\text{Zn}/\text{H}_2\text{SO}_4/\text{MnO}_2$  reserve-primary system.  
↗

#### RÉSUMÉ

Nous décrivons une étude faite sur les propriétés chimiques et électrochimiques des cathodes de bioxyde de manganèse contenant du trioxyde de molybdène. Le bioxyde de manganèse avait été préparé par la décomposition d'un mélange dissous de nitrate de manganèse et d'une quantité minime de trioxyde de molybdène.

Il a été constaté que la composition chimique du bioxyde de manganèse était affectée quand il y avait présence de trioxyde de molybdène à moins de 1%, et dans certains cas, nous avons remarqué une amélioration considérable dans le comportement de décharge d'électrodes fabriquées avec ces oxydes. Les cathodes dopées ont été évaluées en utilisant le système réserve-primaire,  $\text{Zn}/\text{H}_2\text{SO}_4/\text{MnO}_2$ , C.

## INTRODUCTION

In previous work on manganese dioxide cathodes in sulfuric acid (1), the low temperature behaviour of the electrode was found not as satisfactory as might be desired.

This unsatisfactory behaviour is thought to be due to a combination of slow dissolution of reaction products and slow diffusion of hydrogen ions in the interior of the oxide. Only a small fraction of the oxide near the surface is therefore reduced, and low utilization of the electrode results. It was thought that by introducing small amounts of foreign ions, such as  $\text{Mo}^{6+}$ , into the dioxide, an increase in the diffusion rate might be expected, and higher utilization might occur.

The molybdenum-doped manganese dioxide in this work was made by decomposing a solution of manganese nitrate containing molybdenum trioxide. The experimental work is divided into two main sections:

- (1) establishment of the conditions for forming oxides with different compositions and determination of the constituents in them.
- (2) discharge of the electrodes made from the oxides and correlation of the discharge characteristics with the composition.

## EXPERIMENTAL AND RESULTS

### (1) OXIDE PREPARATION

The oxide was made by decomposing 35.8g of a 50% manganous nitrate solution (corresponding to 0.1 mole manganous ions) containing different amounts of molybdenum trioxide. Two different decomposition temperatures were used ( $135^{\circ}\text{C}$  and  $180^{\circ}\text{C}$ ). The time of decomposition was five days. After decomposition, the oxide was ground to pass 60 mesh. The powder was added to 20 ml of 50% ammonia solution and stirred for half an hour. This removed

unreacted molybdenum as ammonium molybdate and precipitated unoxidized manganous ions as manganous hydroxide. After washing first with 50% ammonia solution and then with distilled water, the powder was dried to constant weight.

To determine the constituents of the oxide, a small amount of the oxide was dissolved in a mixture of sulfuric acid and oxalic acid and analysed.

(1.1) Molybdenum in the oxide as a function of the molybdenum trioxide in the manganous nitrate solution

The molybdenum was determined spectrophotometrically with thiocyanate (2). The results, which are shown in Figure 1, (see page 3) show that the amount of molybdenum that goes into the oxide increases with increasing amount of molybdenum trioxide in the manganous nitrate solution and also with increasing temperature. However, a maximum level is reached, most noticeably at 135°C. Whether this maximum level is constant or changes with the time of decomposition has not been determined.

For 135°C the maximum level is near  $10^{-2}$  mole molybdenum per mole manganese. The mole ratio is above  $2 \cdot 10^{-2}$  at 180°C.

(1.2) Available oxygen in the oxide as a function of the molybdenum trioxide in the manganous nitrate solution

In order to determine the available oxygen in the oxide, it was necessary to determine both the total amount of manganese in the sulfuric acid-oxalic acid solution and the amount of the oxalic acid used when the oxide was dissolved. The manganese was determined by adding some of the solution to a strong sodium pyrophosphate solution and titrating with a permanganate solution (3). The oxalic acid used during the dissolution was determined by titrating the remaining oxalic acid with permanganate (4).

A blank determination was made in which only molybdenum trioxide was dissolved in the oxalate solution. Titration showed that no oxalate was used in the dissolution process. The molybdenum ions will therefore not interfere in the analysis.

The results, given in Figure 2, (see page 3) show that the amount of available oxygen decreases towards a limit with increasing amounts of molybdenum trioxide in the manganous nitrate solution. The limit also decreases with increasing temperature. With a decomposition temperature of 135°C the limit is 1.948 (expressed as x in  $\text{MnO}_x$ ). The limit is 1.936 when 180°C is used as a decomposition temperature.

If the results in Figure 1 are compared with the results in Figure 2, it appears that there is a connection between the amount of molybdenum in the oxide and the amount of available oxygen. For either temperature, the higher the molybdenum content of the oxide the lower the amount of available oxygen. This indicates that the molybdenum that goes into the






Figure 1: Fraction of molybdenum in the oxide as a function of the initial fraction in the manganous nitrate solution.




Figure 2: Available oxygen in the oxide as a function of the initial atom ratio Mo/Mn in the manganous nitrate solution.

oxide binds a certain amount of oxygen and renders it unavailable. However, the ratio of bound oxygen to molybdenum is lower for the oxide produced at 180°C than that produced at 135°C. This may be an aging effect, accelerated at the higher temperature.

### (1.3) Manganous ions in the oxide

The electron spin resonance (ESR) method was used to study some of the oxides (5). At 25°C, two waves were found, one broad, corresponding to  $\text{MnO}_2$  and one sharp, corresponding to manganous ions. At 77°K, which is below the Curie point for  $\text{MnO}_2$ , the broad wave disappeared as the oxide changed from a paramagnetic to an anti-ferromagnetic state. The sharp wave was still present, and could be measured without interferences from the wave due to  $\text{MnO}_2$ . In this way the amount of manganous ions present in the different oxides could be determined.

The results of the ESR-measurements are shown in Figure 3 (see page 3). As is seen with the oxides decomposed at 135°C, the amount of manganous ion decreases as the molybdenum trioxide in the manganous nitrate solution is increased. Oxides decomposed at 180°C show no such tendency. As only a few samples were tested, one cannot conclude that this dependence of manganous ion content on the temperature of decomposition has been definitely established.

### (1.4) X-Ray Diffraction Analysis

X-Ray diffraction analysis shows that the oxide has a tetragonal structure corresponding to pyrolusite. No change in the structure was observed when molybdenum was added (6).

Molybdenum free  $\text{MnO}_2$  shows strong fluorescence when a  $\text{CuK}_{\alpha 12}$  filter is used. The fluorescence decreased with increasing molybdenum content, and may be related to the manganous ions present.

## (2) ELECTRODE BEHAVIOUR

### (2.1) Electrode preparation

The electrodes were prepared in the same way as described earlier (1). 1.5g of a 85-15 oxide - graphite mix was pasted with 0.7 ml binder solution (5g carboxymethylcellulose\*, TB-253, dissolved in 300 ml distilled water).

The paste was applied to both sides of a 0.05 mm thick lead foil held in a 1" x 1" Lucite frame. In accordance with procedure in (1) the lead foil was perforated with a series of small holes to promote adhesion of material, and oxidized for 2.5 min. before the paste was applied. After drying an hour before a fan, the pasted electrode was compressed at 7000 psi and dried overnight. For fuller details, the reference (1) above should be consulted.

\*Chemical Developments of Canada Ltd.




Figure 3: Fraction of  $Mn^{2+}$  in the oxide as a function of the initial atom ratio  $Mo/Mn$  in the manganous nitrate solution.

## (2.2) Discharge of the Electrodes

The electrodes were discharged at  $-20^{\circ}\text{C}$  between two zinc sheets in 8N  $\text{H}_2\text{SO}_4$ . The discharge current was 60 mA ( $4.65 \text{ mA/cm}^2$  referred to the geometric area).

The electrodes were allowed to stabilize on open circuit before they were discharged. The end point of discharge was taken as 1.5 volt.

Figure 4 (see page 7) shows some of the best results obtained with different types of oxide. As seen, far better results are obtained using oxides containing molybdenum than using oxides without. The molybdenum containing oxides are even better than the electrolytically formed manganese dioxide. Based on Figure 4, it was found that:

(1) up to 90% more energy (Wh) was obtained when molybdenum-doped manganese dioxide was used instead of manganese dioxide made in the same way, but without molybdenum.

(2) compared with plates made up from battery-grade electrolytic manganese dioxide 10% more energy was obtained.

(3) a higher voltage during the discharge could be obtained when molybdenum-doped manganese dioxide was used instead of electrolytic manganese dioxide.

In Figure 5 (see page 8) the time before 1.5 volt is reached is plotted as a function of the amount of molybdenum trioxide in the manganous nitrate solution. The dots correspond to the average of several experiments.

It is seen that maximum values are obtained for oxides decomposed at both  $135^{\circ}\text{C}$  and  $180^{\circ}\text{C}$ . The value is, however, much lower for oxides decomposed at  $180^{\circ}\text{C}$  than for oxides decomposed at  $135^{\circ}\text{C}$ .

## DISCUSSION

The results show that the presence of molybdenum has a marked effect on the chemical composition as well as on the electrochemical behaviour of manganese dioxide. The decrease in available oxygen with molybdenum increase is too great to be explained merely by a binding of oxygen to the molybdenum (as  $\text{MoO}_3$ ). There is in addition a decrease in manganous ion content which is found at  $135^{\circ}\text{C}$  and which tends to increase the amount of available oxygen. It seems therefore likely that the molybdenum either creates oxygen vacancies or promotes manganese ions into interstitial positions.




Figure 4: Voltage-time curves for commercial electrolytic  $\text{MnO}_2$  and  $\text{MnO}_2$  containing various amounts of molybdenum. Discharges at  $-20^\circ\text{C}$  and at 60 mA.






Figure 5: Runtime as a function of the initial ratio Mo/Mn in the manganous nitrate solution. Discharges at  $-20^{\circ}\text{C}$  and at 60 mA.

The decomposition temperature seems to be of major importance. Although a maximum in the electrode performance is found for both decomposition temperatures (135°C and 180°C), the greatest effect of molybdenum is found at the lowest temperature. Good electrical performance is obtained where the available oxygen is highest and manganous ion concentration is the lowest. The results indicate that both were achieved to a greater extent at 135°C than at 180°C. If still lower temperatures could be used, oxides with even better electrode performance might be obtained.

The best electrodes in this work were prepared from oxides decomposed at 135°C when just sufficient molybdenum had been added to bring both the available oxygen and the manganous ion concentration to their minimum values. (Compare Figs. 2,3, and 5). The exact connection between the molybdenum content and oxide composition on the one side and the electrochemical behaviour on the other side is not yet entirely clear from the existing results. In addition to the parameters already examined, other parameters, such as decomposition temperature and time might also prove to be important. The present report must therefore be treated only as a presentation of preliminary results. Further experiments should be done.

#### ACKNOWLEDGEMENT

The encouragement and help of J.R. Coleman and G.D. Nagy during the course of the work and in the preparation of this note is gratefully acknowledged.

The author is indebted to Dr. C. Gardner, who carried out the ESR measurements and interpreted the results.

## REFERENCES

1. Valand, T. and Coleman, J.: "Manganese Dioxide Cathode in Sulfuric Acid". DREO Invention No. 70-72 (1972).
2. Crouthamel, E.E. and Johnson, C.E. "Thiocyanate Spectrophotometric Determination of Molybdenum and Tungsten". Anal. Chem. 26, 8 (1954).
3. Scribner, W.G. and Anduze, R.A.: "Influence of Diverse Ions on the Determination of Manganese". Anal. Chem. 33, 6 (1961).
4. Freeman, D.S. and Chapman, W.G.: "Improved Oxalate Method for the Determination of Active Oxygen in Manganese Dioxide". Analyst 96, 1194 (1971).
5. Gardner, C.: unpublished results.
6. Brooke, K.W.: Report from Eldorado Nuclear Limited, 21 June, 1972.

UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R & D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall document is classified)		
1. ORIGINATING ACTIVITY  Defence Research Establishment Ottawa ✓	2a. DOCUMENT SECURITY CLASSIFICATION <b>Unclassified</b>	
	2b. GROUP	
3. DOCUMENT TITLE  Molybdenum - Doped Manganese Dioxide for Use as Low Temperature Battery Cathodes. ✓		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) <b>Technical Note</b>		
5. AUTHOR(S) (Last name, first name, middle initial)  T. Valand		
6. DOCUMENT DATE October 1974	7a. TOTAL NO. OF PAGES 12	7b. NO. OF REFS 6
8a. PROJECT OR GRANT NO.  54-80-08	9a. ORIGINATOR'S DOCUMENT NUMBER(S)  DREO Technical Note No. 74-30 ✓	
8b. CONTRACT NO.	9b. OTHER DOCUMENT NO.(S) (Any other numbers that may be assigned this document)	
10. DISTRIBUTION STATEMENT		
11. SUPPLEMENTARY NOTES	12. SPONSORING ACTIVITY	
13. ABSTRACT  UNCLASSIFIED  A study of the chemical and electrochemical properties of manganese dioxide cathodes containing molybdenum trioxide is described. The manganese dioxide was made by the decomposition of a dissolved mixture of manganous nitrate and a small quantity of molybdenum trioxide.  It was found that the chemical composition of the manganese dioxide was affected by the presence of less than 1% molybdenum. In certain cases, considerable improvement was observed in the discharge behaviour of electrodes made with these oxides. The doped cathodes were assessed in the Zn/H <sub>2</sub> SO <sub>4</sub> /MnO <sub>2</sub> reserve-primary system.		

## KEY WORDS

Batteries  
 Battery Electrodes  
 Cathodes  
 Manganese Dioxide  
 Molybdenum - Doped Cathodes  
 Mo-doped MnO<sub>2</sub>  
 MnO<sub>2</sub> cathodes  
 reserve-primary battery  
 Zn/H<sub>2</sub>SO<sub>4</sub>/MnO<sub>2</sub> battery

## INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the organization issuing the document.
- 2a. **DOCUMENT SECURITY CLASSIFICATION:** Enter the overall security classification of the document including special warning terms whenever applicable.
- 2b. **GROUP:** Enter security reclassification group number. The three groups are defined in Appendix 'M' of the DRB Security Regulations.
3. **DOCUMENT TITLE:** Enter the complete document title in all capital letters. Titles in all cases should be unclassified. If a sufficiently descriptive title cannot be selected without classification, show title classification with the usual one-capital-letter abbreviation in parentheses immediately following the title.
4. **DESCRIPTIVE NOTES:** Enter the category of document, e.g. technical report, technical note or technical letter. If appropriate, enter the type of document, e.g. interim, progress, summary, annual or final. Give the inclusive dates when a specific reporting period is covered.
5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the document. Enter last name, first name, middle initial. If military, show rank. The name of the principal author is an absolute minimum requirement.
6. **DOCUMENT DATE:** Enter the date (month, year) of Establishment approval for publication of the document.
- 7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.
- 7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the document.
- 8a. **PROJECT OR GRANT NUMBER:** If appropriate, enter the applicable research and development project or grant number under which the document was written.
- 8b. **CONTRACT NUMBER:** If appropriate, enter the applicable number under which the document was written.
- 9a. **ORIGINATOR'S DOCUMENT NUMBER(S):** Enter the official document number by which the document will be identified and controlled by the originating activity. This number must be unique to this document.
- 9b. **OTHER DOCUMENT NUMBER(S):** If the document has been assigned any other document numbers (either by the originator or by the sponsor), also enter this number(s).
10. **DISTRIBUTION STATEMENT:** Enter any limitations on further dissemination of the document, other than those imposed by security classification, using standard statements such as:
  - (1) "Qualified requesters may obtain copies of this document from their defence documentation center."
  - (2) "Announcement and dissemination of this document is not authorized without prior approval from originating activity."
11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.
12. **SPONSORING ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring the research and development. Include address.
13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document, even though it may also appear elsewhere in the body of the document itself. It is highly desirable that the abstract of classified documents be unclassified. Each paragraph of the abstract shall end with an indication of the security classification of the information in the paragraph (unless the document itself is unclassified) represented as (TS), (S), (C), (R), or (U).  
  
The length of the abstract should be limited to 20 single-spaced standard typewritten lines, 7½ inches long.
14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a document and could be helpful in cataloging the document. Key words should be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context.